

The Supplier should always follow any Customer flow downs or drawing specific requirements first. When these requirements or drawings do not specify, AIT specifications apply. AIT specifications for multiple types of surface coatings, stress relief, or heat treating for machined and fabricated parts can be found at the link below: https://www.aint.com/about_ait/quality/overview

The latest specification available at the link above applies unless otherwise noted on the PO.

If the Supplier believes there to be a conflict between any requirements, please contact the Buyer.

General Requirements

Coating Type	AIT Reference Code	Standard Reference	Applicable Materials
Hard Chrome Plating	HCP	See PO, if applicable	Steel, Stainless Steel, and Aluminum
Product Name		Manufacturer / Distributor	
Not Specified		Not Specified	

Surface Preparation

1. Hand sand/wire brush, as required, to remove surface rust, metal scale and give abrasion to smooth surfaces.
 - a. Wash with xylene using a brush to remove loose particulates.
 - b. Dry part using compressed air.
2. Mask surfaces, as required.
3. Glass Bead, only if required by PO
4. Forward to coating process for chemical cleaning.

Finish

Thickness	Appearance	Texture	Hardness
As per PO - stated as a range, minimum thickness, or per final drawing dimensions.	Uniform	Smooth	66-68HRC
Workmanship / Surfaces		Application	
The coating shall be smooth, adherent, uniform in appearance, and free from blisters, pits, nodules, flaking, and other defects that may affect the function of the coating.		Apply coating to all casting & fabrication surfaces that do not require masking per PO.	

Notes

1. Maintain all AIT tags and markings as supplied.
2. Remove all plugs and masking prior to shipping.



Supply Chain Specification
Coating Specification for Hard Chrome Plating

Document #
SCS-008

Revision
0

DCC #
DCC0000106

Revision History

Rev.	Date	DCC	Comments	Approved By
0	8-8-2023	DCC0000106	Initial release	Robert Chianese